



LEATHER




The gives values, provide general informations and are not part of product specifications.

Notes:
AC: Acrylic PU Copolymer
ACP: Acrylic Polymer
AL: Aliphatic
AR: Aromatic
BCS: Butyl Glycole
DMM: Dipropylene glycole-Dimethylether
MP: Methoxy Propanol
PC: Polycarbonate Diols
PE: Polyether Diols
PES: Polyester Diols
PRC: Propilene Carbonate



Aqueous Polyurethane Dispersions for Leather Coatings

ANIONIC Aliphatic PUD	Isocyanate Type	Polyol Type	Co-solvent Type	Solid Content %	Adhesion Promoter	Base-Coat	Top-Coat	Spray	Roll-Coating	Clothing Industry	Uphol-stery	Shoe Upper	Car Uphol-stery	Hand Modifier	Cross-linker	Thickner
	Chemical Properties				Applicative technology and fields											
ERCAPUR 1150	AL	PES	BCS	30	•	•		•		•	•	•				
ERCAPUR 1150 NF	AL	PES	DMM	30	•	•		•		•	•	•				
ERCAPUR 1155 NF	AL	PE	DMM	26	•	•		•		•	•	•	•			
ERCAPUR 1180	AR	PE	SOLVENT FREE	28	•	•		•			•	•	•			
ERCAPUR VF	AL	PE	SOLVENT FREE	30		•	•	•	•		•	•	•			
ERCAPUR 3000	AL	PC/PE	SOLVENT FREE	40		•		•	•		•		•			
ERCAPUR 5600	AL	PE	SOLVENT FREE	35		•		•	•		•	•	•			
ERCAPUR 6000	AL	PE	DMM	35		•	•	•	•		•	•	•			
ERKAPUR FK/P	AL	PE	DMM	37		•	•	•	•			•	•			
ERCAPUR RG	AL	PES/AC	SOLVENT FREE	40		•		•		•	•	•				
ERCAPUR TE	AL	PE	SOLVENT FREE	30		•	•	•		•		•				
ERCAPUR TH	AL	PE	SOLVENT FREE	35			•	•	•		•	•				
ERCAPUR XP 4803	AL	PE	DMM	36			•	•	•		•		•			
ERCAPUR PR	AL	PE	SOLVENT FREE	35		•	•	•	•		•	•				



Aqueous Polyurethane Dispersions for Leather Coatings

ANIONIC Aliphatic PUD	Chemical Properties				Applicative technology and fields													
	Isocyanate Type	Polyol Type	Co-solvent Type	Solid Content %	Adhesion Promoter	Base-Coat	Top-Coat	Spray	Roll-Coating	Clothing Industry	Upholstery	Shoe Upper	Car Upholstery	Hand Modifier	Cross-linker	Thickner		
ERCAPUR SU	AL	PES	SOLVENT FREE	30			•	•	•	•		•	•					
ERCAPUR M 100/N	AL	PES	DMM	30				•	•	•		•	•					
ERCAPUR BD	AL	PE	DMM	35				•	•	•	•	•	•					
ERCAPUR BX	AL	PE	DMM	30				•	•	•	•	•	•					
ERCAPUR DM 3	AL	PE	DMM	34				•	•	•		•	•	•				
ERCAPUR CLR	AL	PES	SOLVENT FREE	50			•		•	•		•						
ERCAPUR FK/Z	AL	PE	DMM	37			•	•	•	•		•	•	•				
HYDROTECH VLT 384	AR	PE	Very Low VOC *	20	•				•		•	•	•	•				
HYDROTECH VLT 317 AL/20	AL/AR	PE	Very Low VOC *	20	•				•		•	•	•	•				
HYDROTECH VLT 318	AL	PE	DMM	30	•				•		•	•	•	•				
HYDROTECH VLT 108 SS	AR	PE	Very Low VOC *	30	•					•		•	•	•				
HYDROTECH AD 21	AL	PE	Very Low VOC *	35	•													
HYDROTECH LT 326	AL/AR	PE	Very Low VOC *	30			•			•		•	•					



Aqueous Polyurethane Dispersions for Leather Coatings

ANIONIC Aliphatic PUD	Chemical Properties				Applicative technology and fields													
	Isocyanate Type	Polyol Type	Co-solvent Type	Solid Content %	Adhesion Promoter	Base-Coat	Top-Coat	Spray	Roll-Coating	Clothing Industry	Upholstery	Shoe Upper	Car Upholstery	Hand Modifier	Cross-linker	Thickner		
HYDROTECH LT 141	AL	PE	Very Low VOC *	30														
HYDROTECH MT 426	AL	PE	Very Low VOC *	35														
HYDROTECH MT 480	AL	PE	SOLVENT FREE	40														
HYDROTECH MT 1450	AL	PE	DMM	30														
HYDROTECH MT 1455	AL	PE	DMM	30														
HYDROTECH MT 1693	AL	PC	DMM	25														
HYDROTECH XP 4933	AL	PE	DMM	35														
HYDROTECH VHT 1572	AL	PES	DMM	30														
HYDROTECH VHT 1577	AL	PES	DMM	30														
HYDROTECH VHT 1688	AL	PC	DMM	25														
HYDROTECH VHT 1715	AL	PC/PES	Very Low VOC *	35														
HYDROTECH VHT 1774	AL	PE	DMM	35														
HYDROTECH VHT 5016	AL	PES/PE	DMM	35														



Aqueous Polyurethane Dispersions for Leather Coatings

ANIONIC Aliphatic PUD	Isocyanate Type	Polyol Type	Co-solvent Type	Solid Content %	Adhesion Promoter	Applicative technology and fields												
						Base-Coat	Top-Coat	Spray	Roll-Coating	Clothing Industry	Upholstery	Shoe Upper	Car Upholstery	Hand Modifier	Cross-linker	Thickner		
HYDROTECH VHT 4499	AL	PES	DMM	35														
HYDROTECH VHT 4728	AL	PES	DMM	40														
FLEX PU D 5028	AR	PES	DMM	28	•													
FLEX PU DF 3030	AL	PES	DMM	30	•													
FLEX PU D 129	AL	PES	DMM	29	•													
FLEX PU 237	AL	PE	Very Low VOC *	37														
FLEX PU EN 392	AL	PE	Very Low VOC *	40														
FLEX PU E 343	AL	PE/PES	Very Low VOC *	39														
FLEX PU E 39	AL	PE	Very Low VOC *	35														
FLEX PU D 388	AL	PES	DMM	35														
FLEX PU 3535 E	AL	PE	SOLVENT FREE	35														
FLEX PU D 4230	AL	PE	DMM	30														
FLEX PU 136	AL	PES	DMM	35														



Aqueous Polyurethane Dispersions for Leather Coatings

ANIONIC Aliphatic PUD	Isocyanate Type	Polyol Type	Co-solvent Type	Solid Content %	Adhesion Promoter	Applicative technology and fields												
						Base-Coat	Top-Coat	Spray	Roll-Coating	Clothing Industry	Upholstery	Shoe Upper	Car Upholstery	Hand Modifier	Cross-linker	Thickner		
FLEX PU 4330 DT 2	AL	PES	DMM	35				•	•	•		•	•	•				
FLEX PU D 139	AL	PE/PES	DMM	39					•	•	•			•				
FLEX PU 840 EP 8	AL	PC	Very Low VOC *	36					•	•			•		•			

CATIONIC PUD	Chemical Properties				Applicative technology and fields													
	Isocyanate Type	Polyol Type	Co-solvent Type	Solid Content %	Adhesion Promoter	Base-Coat	Top-Coat	Spray	Roll-Coating	Clothing Industry	Upholstery	Shoe Upper	Car Upholstery	Hand Modifier	Cross-linker	Thickner		
ERCAPUR K 300	AL	PES	BCS	30	•			•		•		•	•	•				
ERCAPUR K 300 NF	AL	PES	DMM	30	•			•		•		•	•	•				
ERCAPUR K 340	AL	PE	BCS	30	•			•		•		•	•	•				
ERCAPUR K 1000	AL	PES	SOLVENT FREE	30	•			•		•		•	•	•				
ERCAPUR K 330	AL	PES	BCS	40				•		•		•	•	•				
ERCAPUR K 2000	AL	PE	SOLVENT FREE	30	•			•		•		•	•	•				
FLEX PU DK 2149	AL	PE	DMM	30	•			•		•	•	•	•	•				
FLEX PU DK 37	AL	PES	DMM	30				•		•		•	•	•				



Aqueous Polyurethane Dispersions for Leather Coatings

NON IONIC PUD	Chemical Properties				Applicative technology and fields													
	Isocyanate Type	Polyol Type	Co-solvent Type	Solid Content %	Adhesion Promoter	Base-Coat	Top-Coat	Spray	Roll-Coating	Clothing Industry	Upholstery	Shoe Upper	Car Upholstery	Hand Modifier	Cross-linker	Thickner		
ERCAPUR SK	AL	PE	SOLVENT FREE	30				•		•		•						
ERCAPUR SKD/N	AL	PES	DMM	30	•			•		•		•						
HYDROTECH XP 3193	AL	PE	Very Low VOC *	40				•		•		•		•				
FLEX PU D 3330 S	AL	PES	DMM	30	•			•		•		•						
FLEX PU Y12/30	AL	PE	Very Low VOC *	30				•		•		•						
FLEX PU Y 13	AL	PE	DMM	30	•			•		•		•		•				
FLEX PU D 3330	AL	PES	DMM	30	•			•		•		•						
FLEX PU D 3430	AL	PES	DMM	30				•		•		•						
FLEX PU DN 121	AL	PE	DMM	30				•		•		•						

MATT PUD	Chemical Properties				Applicative technology and fields													
Isocyanate Type	Polyol Type	Co-solvent Type	Solid Content %	Adhesion Promoter	Base-Coat	Top-Coat	Spray	Roll-Coating	Clothing Industry	Upholstery	Shoe Upper	Car Upholstery	Hand Modifier	Cross-linker	Thickner			
HYDROMATT 5135	AL	PE	Very Low VOC *	35						•		•						
HYDROMATT 5050	AL	PE	Very Low VOC *	34						•		•		•				
HYDROTECH XP 5196 MATT	AL	PES	DMM/BCS	25						•		•		•				



Aqueous Polyurethane Dispersions for Leather Coatings

SPECIALTIES	Isocyanate Type	Polyol Type	Co-solvent Type	Solid Content %	Adhesion Promoter	Base-Coat	Top-Coat	Spray	Roll-Coating	Clothing Industry	Upholstery	Shoe Upper	Car Upholstery	Hand Modifier	Cross-linker	Thickner
ERCAPUR AD 40	AL	PE	BCS-MP	40												•
ERCALINK 70	AL	PE	PRC	70											•	
ERCALINK 100	AL	PE	SOLVENT FREE	100											•	
HYCAT WB 70	AL		PRC	70												•
HYCAT WB 100	AL		SOLVENT FREE	100												•
HYCAT WB 4361	AL		DMM/PRC	70												•